

# PRODUCT DATA SHEET



## GLOBAL HRC

Heat Reflective Coating

GLOBAL HRC is an innovative water based heat reflective coating formulated from acrylic polymers for maximum heat reflectivity and durability. The coating is an ideal primary heat barrier when applied to external surfaces such as roofs, walls of buildings, storage facilities and enclosures. The major application of Global HRC is in the reduction of internal temperatures (and an associated reduction in internal pressure) of the bulk grain storages of the various state grain handling authorities such as Co-operative Bulk Handling Ltd in Western Australia, Grain Corporation of new South Wales, Victoria and Queensland. In this extremely harsh environment, Global HRC has proven its superb durability, low chalking rate, dirt pick up resistance and UV tolerance, whilst reducing internal temperatures within these storages by between 10°C and 15°C. In order to achieve maximum heat reflectivity Global HRC is produced in brilliant white only. The product can be tinted to a wide range of colours for use wherever a high performance decorative or protective coating is required; however, the heat reflective properties diminish acutely with the introduction of colour. This easily applied coating has specific adhesion properties for application to galvanized steel, concrete and masonry.

### Physical Characteristics

Product type	Solvent-free dispersion of modified acrylic resins with mineral fillers and lightfast pigments
Appearance	Viscous liquid. White, may be coloured
Viscosity@25°C	4000-5000 mPa
Density @ 25°C	1.25Kg/Lt
pH	>9.0
Solids	Approximately 52% by weight
Application Rate	Approximately 6m <sup>2</sup> /Lt @ 50 microns D.F.T Recommended 2.0-2.5m <sup>2</sup> /Lt to achieve 150micron D.F.T
Film Appearance	Low Sheen
Susceptibility to Frost	Avoid freezing conditions. Store above +2°C
Storage Stability	2 Years or more in suitable conditions (18°C to 50 °C)
Cleaning Agent	Water
Danger Classification	Not Applicable. Non Hazardous.

## Application Information

Surface Preparation	Surface must be clean, stable and free of oil and grease. Loose particles should be removed and repairs carried out if required. Unweathered metal or powdercoated surfaces should be sealed with an approved sealer/primer
Application Conditions	Do not apply if the ambient temperature is below 10°C or during rain or if the temperature of the surface may fall below 10°C during the drying period. Do not apply when ambient and substrate temperatures are above 38°C. Do not apply if the relative humidity is above 85% or if dew point is likely to be reached during the drying period.
Application Process	By brush or paint roller. Sprayable with airless spray equipment at 5 bar pressure and minimum 0.21mm to 0.30mm nozzle size.
Application Rate	Approximately 6m <sup>2</sup> /Lt @ 50 microns D.F.T Recommended 2.0-2.5m <sup>2</sup> /Lt to achieve 150 microns D.F.T. This should be applied in two or more coats
Drying	Will vary with air temperature, humidity and air circulation. In normal conditions, may be touch dry in 1 to 3 hours (depending on thickness of application) and recoatable after a minimum of 4 hours. Under adverse conditions, drying will be impaired and in extreme instances, may even not be possible.

## Equipment Cleanup:

Wash all equipment thoroughly with water.

## Safety Precautions:

Avoid ingestion and contact with skin or eyes. Wear protective goggles and waterproof gloves.

## Pack Sizes:

20 litres, 200 litres, 1000 litres

## Contact Point

For further information and technical assistance please contact:

Uniseal Manufacturing  
17 Ryelane Street  
Maddington WA 6109  
Tel: 1300 577 719  
Fax: 1300 366 353  
Email: [uniseal@sealingservices.com.au](mailto:uniseal@sealingservices.com.au)  
[www.unisealcoatings.com.au](http://www.unisealcoatings.com.au)



Uniseal Manufacturing is a division  
of the Global Group of Companies

DISCLAIMER: Please note that this information is supplied based on field and laboratory tests and is, to the best of our knowledge, deemed to be correct, however, no guarantee of the accuracy of this information in all instances is intended or implied and Uniseal Manufacturing accepts no liability for any failure or loss that may result from the application process. Please contact Uniseal Manufacturing if additional or task-specific information is required.