



PRODUCT DATA SHEET

SUPAPRIME

SUPAPRIME is a single pack water based sealer and binding agent formulated for use on a variety of substrates. Based on special water based adhesion promoted resins and additives Supaprime is designed for sealing Supaboard panels, Concrete, Gyprock, Masonry, Fibre Cement, Magnesium Oxide and Calcium Silicate boards and Aluminium surfaces.

Physical Characteristics

Product type	Solvent-free dispersion of modified acrylic resins
Appearance	Light Green liquid.
Viscosity@25°C	2000 mPa
Density @ 25°C	1.02 Kg/Lt
Solids	Approximately 25%
Application Rate	Approximately 8-14m ² /LT @ 20 micron DFT Recommended Application rate 10m ² /LT
Susceptibility to Frost	Avoid freezing conditions. Store above +2°C
Storage Stability	2 Years or more in suitable conditions (18°C to 50 °C)
Cleaning Agent	Water
Danger Classification	Not Applicable. Non Hazardous.

Application Information

Surface Preparation	Surface must be clean, stable and free of oil and grease. Loose particles should be removed and repairs carried out if required.
Application Conditions	Do not apply if the ambient temperature is below 10°C or during rain or if the temperature of the surface may fall below 10°C during the drying period. Do not apply when ambient and substrate temperatures are above 38°C. Do not apply if the relative humidity is above 85% or if dew point is likely to be reached during the drying period. High humidity and low temperatures will affect cure time.

Application Information - continued

Application Process Do not dilute. Apply by brush or paint roller and via airless spray equipment at 5 bar pressure and a minimum 0.21mm to 0.30mm nozzle size.

Mask exposed glass surfaces to avoid overspray as product may be difficult to remove

Equipment Cleanup:

Wash all equipment thoroughly with water.

Safety Precautions:

Avoid ingestion and contact with skin or eyes. Wear protective goggles and waterproof gloves.

Pack Sizes:

20 litres, 200 litres, 1000 litres

Contact Point

For further information and technical assistance please contact:

Uniseal Manufacturing
17 Ryelane Street
Maddington WA 6109
Tel: 1300 577 719
Fax: 1300 366 353
Email: uniseal@sealingservices.com.au
www.unisealcoatings.com.au



Uniseal Manufacturing is a division
of the Global Group of Companies

DISCLAIMER: Please note that this information is supplied based on field and laboratory tests and is, to the best of our knowledge, deemed to be correct, however, no guarantee of the accuracy of this information in all instances is intended or implied and Uniseal Manufacturing accepts no liability for any failure or loss that may result from the application process. Please contact Uniseal Manufacturing if additional or task-specific information is required.